

Del bloque forjado en plano, cuadrado y garantizamos la ejecución correcta según los planos y dibujos

Aceros inoxidables

Material	DIN	AISI/ASTM
1.4006	F3401	AISI 410
1.4021	F310J	AISI 420
1.4028	X30Cr13	AISI 420
1.4031*	F3403	AISI 420
1.4034	F3405	AISI 420
1.4057	F313	AISI 431
1.4104	F3413	AISI 430F
1.4112	X90CrMoV18	AISI 440B
1.4122	X39CrMo17-1	
1.4125	X105CrMo17	AISI 440C
1.4301	F3504	AISI 304
1.4305	F310	AISI 303
1.4306	X2CrNi19-11	AISI 304L
1.4307	X2CrNi18-9	AISI 304L
1.4313	X3CrNiMo13-4	ASTM A182 F6NM 430F
1.4401	F310A	AISI 316
1.4404	F310K	AISI 316L
1.4410**	X2CrNiMoN25-7-4	ASTM A182 F53
1.4418	X4CrNiMo16-5-1	
1.4429	X2CrNiMoN17-13-3	AISI 316LN
1.4435	X2CrNiMo18-14-3	AISI 316L
1.4462**	X2CrNiMoN22-5-3	AISI 318 LN ASTM A182 F51
1.4539	X1CrNiMoCu25-20-5	AISI 904L
1.4541	F332	AISI 321
1.4542	F310B	AISI 630
1.4548	X5CrNiCuNb17-4-4	AISI 630
1.4550	X6CrNiNb18-10	AISI 347
1.4571	X6CrNiMoTi17-12-2	AISI 316Ti

Aceros resistentes a altas temperaturas

Material	DIN	AISI/ASTM
1.4903	X10CrMoVNb9-1	ASTM A182
1.4923	X22CrMoV12-1	

Aceros de herramienta

Material	DIN	AISI/ASTM
1.1730	C45U	AISI 1045
1.2080	X210Cr12	AISI D3
1.2083	F3404	AISI 420
1.2085	X33CrS16	AISI 420FM
1.2311	F5303	AISI P20
1.2312	F5302	AISI P20+S
1.2316	X36CrMo17	AISI 420
1.2343*	X37CrMoV5-1	AISI H11
1.2344*	F5318	AISI H13
1.2358	60CrMoV18-5	
1.2379*	X153CrMoV12	AISI D2
1.2436	X210CrW12	AISI D6
1.2510	100MnCrW4	AISI O1
1.2714	F5307	AISI L6
1.2738	40CrMnNiMo8-6-4	AISI P20+Ni
1.2767	45NiCrMo16 X45NiCrMo4	
1.2842	90MnCrV8	AISI O2

Aceros de cementación y nitruración

Material	DIN	AISI/ASTM
1.5752	F1540 F154	AISI 3310
1.6587	18CrNiMo7-6	AISI 4820
1.8519	F1721	
1.8550	34CrAlNi7-10	

Aceros bonificados

Material	DIN	AISI/ASTM
1.0503	F114 C45	AISI 1045
1.0764	36SMn14	
1.1221	C60E	
1.6511	36CrNiMo-4	AISI 4340
1.6580	30CrNiMo8	AISI 4340
1.6582	F1272	AISI 4340
1.6587	18CrNiMo7-6	AISI 4820
1.6773	36NiCrMo16	
1.7218	F222	AISI 4130
1.7225	F1252 F125	AISI 4140
1.7707	30CrMoV9	AISI 4340
1.8159	F1430 F143	AISI 6150

Aceros refractarios

Material	DIN	AISI/ASTM
1.4713	X10CrAlSi7	
1.4841	F3310	AISI 314
1.4878	X8CrNiTi18-10	AISI 321 H

Aceros termorresistentes

Material	DIN	AISI/ASTM
1.0460	P250GH	ASTM A105
1.6981	21CrMoNiV4-7	
1.7335	13CrMo4-5	ASTM A182 F11
1.7380	10CrMo9-10	

Acero para rodamiento

Material	DIN	AISI/ASTM
1.3505	100Cr6	AISI 52100

Aceros estructurales de grano fino

Material	DIN	AISI/ASTM
1.8928	S690QL	

Aceros especiales


Material	DIN	AISI/ASTM
1.6565	F1275	AISI 4340
1.6957	26NiCrMoV14.5	

Aleación a base de níquel

Material	DIN	AISI/ASTM
2.4858		Alloy 825

* en calidad ESU

** DUPLEX | SUPER DUPLEX



De las chapas laminadas

Aceros inoxidables

Material	Espesor
1.4112 AISI 440B X90CrMoV18	3 - 10 mm, laminado, recodido
1.4301 AISI 304 F3504	10 - 120 mm, laminado
1.4305 AISI 303 F310	10 - 32 mm, laminado
1.4307 AISI 304L X2CrNi18-9	10 - 120 mm, laminado
1.4401 AISI 316 F310A	10 - 120 mm, laminado 100 - 500 mm, forjado
1.4404 AISI 316L F310K	10 - 120 mm, laminado 100 - 500 mm, forjado

Aceros termorresistentes

Material	Espesor
1.7335 13CrMo4-5	10 - 80 mm, laminado
1.7380 10CrMo9-10	10 - 80 mm, laminado

German Special Steel S.L.
Avda. del Plá 126, local 1.25
E-03730 Jávea | Alicante

Gaby Path | Gerente

Tel.: + 34 965 793 934

Mobil: + 34 606 035 759

skype: gssjavea

E-Mail: info@gss-spain.com

Acero de bonificación / chapa negra / tratada

Material	Espesor
1.0503 C45 F114	10 - 150 mm, laminado
1.0601 C60	10 - 150 mm, laminado
1.1221 C60E	10 - 130 mm, laminado
1.1730 C45U	180 - 350 mm, forjado
1.7225 AISI 4140 42CrMo4 F1252 F125	15 - 100 mm, laminado, bonificado 300 - 400 mm, forjado, bonificado

Aceros de cementación y nitruración

Material	Espesor
1.7131 1.7147 16MnCr5 F20MnCr5 F1516 F150D	10 - 150 mm, laminado 180 - 300 mm, forjado



Redondo forjado

Aceros inoxidables

Material	Diámetros disponibles
1.4021 AISI 420 F310J	von Ø 150 bis Ø 1010 mm
1.4024 AISI 410 - 420	von Ø 160 bis Ø 540 mm
1.4034 AISI 420 X46Cr13	von Ø 100 bis Ø 153 mm
1.4112 AISI 440B X90CrMoV18	von Ø 95 bis Ø 350 mm
1.4122 X39CrMo17-1	von Ø 121 bis Ø 140 mm
1.4313 X3CrNiMo13-4	von Ø 75 bis Ø 1300 mm
1.4418 X4CrNiMo16-5-1	von Ø 405 bis Ø 705 mm
1.4541 AISI 321/ F332	von Ø 300 bis Ø 486 mm

Aceros termorresistentes

1.6981 21CrMoNiV4-7	von Ø 267 bis Ø 640 mm
1.7335 13CrMo4-5	von Ø 257 bis Ø 500 mm
1.7709 21CrMoV5-7	von Ø 200 bis Ø 305 mm

Acero resistente a altas temperaturas

1.4923 X22CrMoV12-1	von Ø 225 bis Ø 620 mm
-----------------------	------------------------

Acero de bonificación

1.7225 AISI 4140 42CrMo4 F1252 F125



DIN EN ISO 9001 : 2008
zertifiziert seit 1998

